



**PRODUCT SPECIFICATION**  
THE GOODYEAR TIRE & RUBBER CO.  
GOODYEAR CHEMICAL AKRON , OH 44306-3299  
USA: 1-800-548-8107

**POLYSTAY 29**

Description : POLYSTAY 29 is a mixture of styrenated diphenylamines at 99+% concentration .

---

PROPERTY	LIMITS	TEST METHOD
Appearance	clear viscous liquid - amber/material will occasionally refracts light to give green tint	visual
Gardner Color	<= 7	BP-WI-0293
Refractive index @ 25 C	1.6378 +/- 0.0013	BP-WI-0102
para-substitution , %	72.5 +/- 7.5	BP-WI-0056
Styrene/Diphenylamine Ratio	2.10 +/- 0.15	BP-WI-0056
Brookefield viscosity @ 25 C, cPs	30,000 +/- 10,000	BP-WI-0116

Goodyear test methods are available upon request .

Check with your Goodyear salesperson to confirm the revision number of the most recent specification .